



Issued to:

MODERATE SPACE PRIVATE LIMITED,
PLOT NO.94, Renuka Sahasra Enclave, Keesara Road
Kundanpally X Road Bus Stop, Kundanpally,
Hyderabad, Medchal Malkajgiri, 501301.

ULR : NABL T0726TS185562620000296

Report No.: LL/26-27/006763

Issue Date: 29/08/2026.

Customer Ref: Test Request Form

Ref.Date: 19/08/2026.

Sample Particulars: **NEUTRAL SALT SPRAY (NSS) TEST SPECIMEN.**

Sample Description: SS Wire (SS 316).

Quantity: 1No. Packing: packed in polythene cover. Sample Condition: Ambient.

Test Required: Neutral Salt Spray (NSS) test for 48 hours as per ISO 9227.

Date of receipt of sample : 19/08/2026.

Date of starting of analysis : 25/08/2026.

Date of completion of analysis : 27/08/2026.

TEST RESULTS

Sl.No.	Test Parameters	UOM	Requirement as per ISO 9227:2022	Results
Discipline: Electronics				
Group: Environmental Test Facility				
I.	Neutral Salt Spray Solution details			
a	Solution type	--	--	Sodium Chloride
b	Water Used	--	--	Distilled water
c	Sodium chloride concentration	g/l	50 ± 5	51
d	Chamber temperature	°C	35 ± 2	35
e	Collection rate of sprayed solution area 80cm ²	ml/h	1.5 ± 0.5	1.59
f	pH of collected solution	-	6.5 – 7.2	6.77

Sl.No	Sample ID	UOM	Results
II.	Neutral Salt Spray test for 48 Hours	Visual	The submitted samples subjected to neutral salt spray test for 48Hours and found free from pitting and rust formation.

Test Method: As per ISO 9227:2022.

Note1: The report and results relate only to the samples/items tested.

End of Report


P.J. VIJAY KUMAR
Reviewed by

Page 1 of 1


J.UDAY KUMAR
AUTHORIZED SIGNATORY

169944

Note: This report is subject to the terms and conditions mentioned overleaf